

Eurofins Umwelt Ost GmbH - Lindenstraße 11  
Gewerbegebiet Freiberg Ost - D-09627 - Bobritzsch-Hilbersdorf

**Hanse-Pellet GmbH & CO. KG**  
**Ritscherstr. 20**  
**21244 Buchholz**

Title : **Extract from (Batch): AR-18-FR-004789-01 (11804395)**  
Test report number : **EX-18-FR-000394-01**

Project name : **Untersuchung von Pellets**

Number of samples : **1**  
Sample type : **wood pellets**  
Sample Taker: **Client**  
Sample reception date : **2018-02-21**  
Sample processing time : **2018-02-21 - 2018-03-05**

The test results refer solely to the analysed test specimen. Unless the sampling was done by our laboratory or in our sub-order the responsibility for the correctness of the sampling is disclaimed. This test report is only valid with signature and may only be further published completely and unchanged. Extracts or changes require the authorisation of the EUROFINS UMWELT in each individual case.

Our General Terms & Conditions of Sale (GTCS) are applicable, as far as no specific agreements do exist. The GTCS are available on <http://www.eurofins.de/umwelt/avb.aspx>.

Accredited test laboratory according to DIN EN ISO/IEC 17025 notification under the DAkkS German Accreditation System for Testing. The laboratory is according (D-PL-14081-01-00) accredited.

Dr. Ulrich Erler  
Analytical Service Manager  
Phone +49 3731 2076 510

Digitally signed 05.03.2018  
Dr. Ulrich Erler  
Prüfleitung



Parameter	Lab	Accr.	Method	Limit values						Description		MP: Analyse Quartal I 2018	
				ENplus A1 ar	ENplus A1 db	ENplus A2 ar	ENplus A2 db	ENplus B ar	ENplus B db	Sample number		118015563	
				LOQ	Unit	ar	db						
<b>Quality characteristics</b>													
Length	FR		DIN EN ISO 17829									übereinstimmend	-
Diameter	FR		DIN EN ISO 17829	1)		1)		1)			mm	6.1	-
Moisture	FR	JE02	DIN EN ISO 18134-2	10		10		10		0.1	% (w/w)	6.5	-
Ash content (550°C)	FR	JE02	DIN EN ISO 18122		0.7		1.2		2	0.1	% (w/w)	-	0.3
Durability	FR	JE02	DIN EN ISO 17831-1	≥ 98		≥ 97.5		≥ 97.5			% (w/w)	99.4	-
Fine portion < 3,15 mm	FR	JE02	DIN EN ISO 18846	1 <sup>2)</sup>		1 <sup>2)</sup>		1 <sup>2)</sup>		0.1	% (w/w)	< 0.1	-
Bulk density	FR	JE02	DIN EN ISO 17828	600 - 750		600 - 750		600 - 750			kg/m <sup>3</sup>	636	-
Net calorific value (qp,net)	FR	JE02	berechnet nach DIN EN ISO 18125	≥ 16.5 <sup>3)</sup>		≥ 16.5 <sup>3)</sup>		≥ 16.5 <sup>3)</sup>		0.200	MJ/kg	18.0	-
Nitrogen	FR	JE02	DIN EN ISO 16948		0.3		0.5		1	0.05	% (w/w)	-	0.07
Sulphur	FR	JE02	DIN EN ISO 16994		0.04		0.05		0.05	0.005	% (w/w)	-	0.008
Chlorine	FR	JE02	DIN EN ISO 16994		0.02		0.02		0.03	0.005	% (w/w)	-	< 0.005
<b>Minor elements acc. DIN EN ISO 16968</b>													
Arsenic (As)	FR	JE02	DIN EN ISO 17294-2		1		1		1	0.8	mg/kg	-	< 0.8
Lead (Pb)	FR	JE02	DIN EN ISO 17294-2		10		10		10	2	mg/kg	-	< 2
Cadmium (Cd)	FR	JE02	DIN EN ISO 17294-2		0.5		0.5		0.5	0.2	mg/kg	-	0.2
Chromium (Cr)	FR	JE02	DIN EN ISO 17294-2		10		10		10	1	mg/kg	-	< 1
Copper (Cu)	FR	JE02	DIN EN ISO 17294-2		10		10		10	1	mg/kg	-	< 1
Nickel (Ni)	FR	JE02	DIN EN ISO 17294-2		10		10		10	1	mg/kg	-	< 1
Mercury (Hg)	FR	JE02	DIN EN ISO 12846		0.1		0.1		0.1	0.05	mg/kg	-	< 0.05
Zinc (Zn)	FR	JE02	DIN EN ISO 17294-2		100		100		100	1	mg/kg	-	8
<b>Ash melting behaviour (ox. atmo.) 815°C</b>													
Shrinkage start temp SST	FR	JE02	analog CEN/TS 15370-1		4)		4)		4)		°C	-	1120
Deformation temp DT	FR	JE02	analog CEN/TS 15370-1		≥ 1200		≥ 1100		≥ 1100		°C	-	1460
Hemisphere temp HT	FR	JE02	analog CEN/TS 15370-1		4)		4)		4)		°C	-	> 1500
Flow temp FT	FR	JE02	analog CEN/TS 15370-1		4)		4)		4)		°C	-	> 1500

## Explanations

LOQ - Limit of quantification

ar - as received

db - dry basis

Lab - Abbreviation of the performing laboratory

Accr. - Abbreviation of the accreditation of the performing laboratory

The parameters identified by FR have been performed by the laboratory Eurofins Umwelt Ost GmbH (Bobritzsch-Hilbersdorf). The accreditation code JE02 identifies the parameters accredited according to DIN EN ISO/IEC 17025:2005 D-PL-14081-01-00 .

## Explanations regarding Limits

Analysis performed according to EN plus (wood pellets) - edition August 2015.

- 1) D06 or D08 pellets +/- 1mm
- 2) at the end of production or by loading vehicles for delivery to the customer ( $\leq 0,5$  for filling in pellet bags or big bags)
- 3) qp,net: net calorific value at constant pressure
- 4) should be given

EUROFINS UMWELT assumes no responsibility for the legal liability of the cited limits.